

WWW.CHITEC.COM

Heat and UV light stabilizer for coatings

1.	General				
	Chiguard [®] 3253 is a synergistic blend of stabilizers specifically designed for coatings. It provides outstanding performance for a wide variety of clear and pigmented coating systems. It is suitable for both water-borne and solvent-borne applications. Its superior effectiveness is particularly pronounced in improved thermal stability, good color maintenance and long-term thermal and UV light stabilization.				
2.	Properties				
	Chemical name Structure	A blend of Chiguard 5530 and Chiguard 353			
	a.				
	L	CH ₂ CH ₂ CO(OCH ₂ CH ₂) _{6⁻⁷} OH			
	b.	$\bigcup_{N} \stackrel{HO}{\longrightarrow} HO$			
	С.				
		$\begin{array}{c} H_{3}C \xrightarrow{CH_{3}} O \xrightarrow{O} O \xrightarrow{H_{3}C} CH_{3} \\ H_{3}C \xrightarrow{-N} O \xrightarrow{-C} O \xrightarrow{-C} (CH_{2})_{8} \xrightarrow{-C} O \xrightarrow{-O} \xrightarrow{-O} N \xrightarrow{-CH_{3}} \\ H_{3}C \xrightarrow{-CH_{3}} O \xrightarrow{-C} O \xrightarrow$			
	d.	$H_{3}C-O-C-(CH_{2})_{8}-C-O-(CH_{2})_{8}-C-O-(CH_{3})_{H_{3}C}CH_{3}$			
	CAS No.	: a. 104810-48-2 b. 104810-47-1 c. 41556-26-7 d. 82919-37-7			



WWW.CHITEC.COM

Heat and	UV	light	stabilizer	for	coatings	
----------	----	-------	------------	-----	----------	--

3.	Physical Data						
	Appearance	:	Pale yellow liquid				
	Odor	:	Odorless				
	Boiling point	:	N/A				
	Specific gravity	:	1.11 (25 °C, g/mL)				
	Viscosity (cps)	:	960 @25 °				
	Color (Gardner)	:	4.1				
	Vapor pressure	:	< 1 mmHg (20 °C)				
4.	Solubility						
	(g in 100 ml solvent	(g in 100 ml solvent @20°C)					
	Butanol	:	>50				
	Butyl acetate	:	>50				
	Ethyl glycol	:	>50				
	MEK	:	>50				
	Styrene	:	>50				
	TMPTA	:	>50				
	Water	:	<0.5				
5.	Specification						
	Appearance	:	Pale yellow liquid				
	Specific gravity	:	1.09~1.13 (25 °C, g/mL)				
	Viscosity	:	1200 max. (25 °C, cps)				
	Volatile	:	0.5% max.				
	Clarity of solution	:	Clear				
	Color (Gardner)	:	6.0 max.				
	Transmittance	:					
	@460 nm	:	95 min.				
	@500 nm	:	97 min.				
6	Suggested Appli	cation					

6. Suggested Application

Chiguard[®] 3253 is especially recommended for the clear and light pigmented applications such as wood coatings, PUR systems, UPES/Styrene gel coats, UV radiation curing systems based on acrylics and UPES. The use levels of Chiguard[®] 3253 range between 0.5% and 4% are recommended for protection. It depends on the substrate and performance requirements of the final application.




PRODUCT DATA SHEET CHIGUARD[®] 3253

WWW.CHITEC.COM

Heat and UV light stabilizer for coatings





8.

³⁰ kg plastic drum / 200 kg steel drum