

Additives for coatings and printing inks  
**DISPARLON®**

July 2024

## DISPARLON® SPX-20CF

(Defoaming/anti-popping agent)

DISPARLON® SPX-20CF is a cumene-free defoaming/anti-popping agent mainly composed of vinyl/acrylic polymers. DISPARLON® SPX-20CF is suitable for high-viscosity/high-build ambient cure coatings used for flooring and waterproofing materials, provides excellent defoaming effect, and may prevent the formation of Bénard cells. DISPARLON® SPX-20CF is also recommended for industrial baking coatings, provides stable defoaming/anti-popping effects since it is unlikely to separate and aggregate during paint circulation, and may improve leveling of the coating film after baking.

### ADVANTAGES

- Excellent defoaming/anti-popping effects
- Anti-flooding/anti-floating effects
- Improves leveling
- Excellent recoatability
- Silicone-free
- Cumene-free

### APPLICATIONS

DISPARLON® SPX-20CF is recommended for high-viscosity/high-build ambient cured coatings (solvent-free epoxy, urethane, etc.) used for floor coatings and waterproofing, and industrial baking coatings (alkyd/melamine, acrylic/melamine, polyester/melamine, urethane, etc.).

### INCORPORATION

- Additive levels : 0.3 – 2.0 wt% on total formulation.  
The optimal additive level should be determined under an actual use condition.
- Method : Can be added at each production stage.  
Post-addition at a final production stage is recommended.

### TYPICAL PROPERTIES

(The following figures are typical properties, not to be used for specification.)

|                      |                                 |
|----------------------|---------------------------------|
| Appearance           | Clear to light yellow liquid    |
| Non-volatile matter  | 20 %                            |
| Density (20 deg.C)   | 0.89 g/cm <sup>3</sup>          |
| Viscosity (20 deg.C) | 4.5 mPa·s                       |
| Solvent              | Solvent naphtha/n-Butyl acetate |

### CAUTION

Precipitation or solidification may occur at low temperature. Store above 0 deg.C.



*Kusumoto Chemicals, Ltd.*

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN  
(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2024 All Rights Reserved By Kusumoto Chemicals, Ltd.