



DISPARLON® A630-20X

Anti-sagging / Anti-settling agent for solvent-borne systems

TECHNICAL DATA SHEET

Issued on 18 September 2026

DISPARLON® A630-20X is a thixotropic agent based on pre-activated amide wax. It can be easily incorporated into a wide range of vehicles and/or solvents and provides exceptionally strong and long-lasting thixotropic properties.

TYPICAL PROPERTIES

The following figures are typical properties, not to be used for specification.

Appearance	Light yellow paste
Non-volatile matter	20 wt%
Solvent	Xylene / Ethanol / Methanol / 2-Propanol

ADVANTAGES

- Provides strong anti-sagging performance, particularly in high-build coatings.
- Ready to use (no activation process required).

APPLICATION

DISPARLON® A630-20X is recommended for most solvent-borne systems, including heavy-duty, marine, industrial, architectural, and wood coatings.

INCORPORATION

Addition levels

The recommended dosage level based on the total formulation is 1.0–5.0 wt% for anti-sagging and 0.5–2.0 wt% for anti-settling.

However, the dosage level may fall outside these ranges depending on the formulation.

The optimal level should be determined under actual use conditions.

Method

Incorporation using a high-speed dissolver is recommended.

Dispersing temperature

The amide component may form particles if it dissolves into the formulation and subsequently precipitates during the dispersing process. To prevent particle formation, the standard dispersing temperature should be between room temperature and 50 °C. Care should be taken with the dispersing temperature, as particles may form at the upper end of this temperature range if the formulation contains a large amount of polar solvent.

STORAGE

Particles may form in the paste during storage at temperatures below 20 °C due to crystallization of the ingredients.

In such cases, please warm the container in a heating chamber at 35 °C to 40 °C for 24 to 48 hours immediately before use.

CAUTION

Recoatibility should be checked, especially in alkyd-melamine or oil-modified alkyd baking systems.



Kusumoto Chemicals, Ltd.

Kusumoto Bldg. 1-11-13 Uchikanda Chiyoda-ku Tokyo,
101-0047 Japan
TEL +81-3-3292-8685

<https://www.kusumoto.co.jp/en/>

The information provided herein is based on data believed to be reliable, but any recommendations or suggestions made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the condition that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by the user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement, or recommendation to practice any patented invention without a license. Please refer to the SDS for safe handling before use.
© 2006–2026 All Rights Reserved By Kusumoto Chemicals, Ltd.