



DISPARLON® 6200

Anti-Slumping agent for Sealants & Adhesives

TECHNICAL DATA SHEET

Issued on 13 July 2026

DISPARLON® 6200 is a powdered thixotropic agent based on amide wax.

When dispersed along with heating, DISPARLON® 6200 builds up a strong thixotropic network in the vehicle and prevents slumping of sealants and adhesives.

TYPICAL PROPERTIES

The following figures are typical properties, not to be used for specification.

Appearance	White to light yellow powder
Melting point	128 °C
Acid value (mgKOH/g)	Max. 8.0
Amine value (mgKOH/g)	Max. 8.0
Particle size	Max. 15 µm
Apparent density	0.15 g/cm ³

ADVANTAGES

- Readily imparts strong anti-slumping properties when dispersed with heat.
- Provides uniform adhesion by preventing slumping.
- Composed of 100% organic matter.
- Provides good handling during application and manufacturing.

APPLICATION

Recommended for sealants (Modified silicone, Urethane, etc.) and Epoxy adhesive systems.

INCORPORATION

Addition levels

0.5–5.0 wt% on total formulation.

The optimal additive level should be determined under actual use conditions.

Dispersing equipment

Adjust the temperature in the range of 55–90 °C.

Addition with a kneader, planetary mixer, or twin-screw extruder is recommended.

The optimum dispersion temperature, time, and shear conditions should be determined under actual processing conditions.

During the cooling process, high shear forces such as those generated by a high-speed dissolver should be avoided.



Kusumoto Chemicals, Ltd.

Kusumoto Bldg. 1-11-13 Uchikanda Chiyoda-ku Tokyo,
101-0047 Japan

TEL +81-3-3292-8685

<https://www.kusumoto.co.jp/en/>

The information provided herein is based on data believed to be reliable, but any recommendations or suggestions made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the condition that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by the user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement, or recommendation to practice any patented invention without a license. Please refer to the SDS for safe handling before use.
© 2012–2026 All Rights Reserved By Kusumoto Chemicals, Ltd.