



DISPARLON® 6650

Thixotropic agent for solvent-borne systems

TECHNICAL DATA SHEET

Issued on 13 July 2026

DISPARLON® 6650 is a powdered thixotropic agent based on amide wax.

When activated in coating systems by applying shear to the mixtures, DISPARLON® 6650 provides thickening, anti-sagging, and anti-settling effects, while maintaining good workability.

TYPICAL PROPERTIES

The following figures are typical properties, not to be used for specification.

Appearance	White to light yellow fine powder
Melting point	122 °C
Acid value (mgKOH/g)	Max. 5.0
Amine value (mgKOH/g)	Max. 5.0
Particle size	Max. 15 µm
Apparent density	0.19 g/cm ³

ADVANTAGES

- Excellent thickening, anti-sagging, and anti-settling properties
- Effective in a wide range of activation conditions
- Good workability
- Excellent recoatability
- Powdered form; 100% active matter

APPLICATION

DISPARLON® 6650 is recommended for general synthetic resin coating systems.

DISPARLON® 6650 is particularly suitable for solvent-borne epoxy and acrylic coating systems, such as marine and heavy-duty anti-corrosion coatings.

INCORPORATION

Addition levels

0.5–3.0 wt% on total formulation.

The optimum additive level should be determined under actual use conditions.

Method

Adjust the temperature in the range of 50–70°C.

Addition using a sand mill and high-speed dissolver is recommended.

The optimum dispersing temperature, time, and shear conditions should be determined under actual use conditions.

Adding 1–2 % of alcohol can lower the optimum dispersion temperature.

After the dispersion process, avoid applying further shear during cooling.



Kusumoto Chemicals, Ltd.

Kusumoto Bldg. 1-11-13 Uchikanda Chiyoda-ku Tokyo,
101-0047 Japan

TEL +81-3-3292-8685

<https://www.kusumoto.co.jp/en/>

The information provided herein is based on data believed to be reliable, but any recommendations or suggestions made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the condition that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by the user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement, or recommendation to practice any patented invention without a license. Please refer to the SDS for safe handling before use.
© 1998-2026 All Rights Reserved By Kusumoto Chemicals, Ltd.