



DISPARLON® TFS-10

Anti-slumping agent for Sealants & Adhesives

TECHNICAL DATA SHEET

Issued on 18 September 2026

DISPARLON® TFS-10 is a powdered thixotropic agent based on amide wax. DISPARLON® TFS-10 can be activated in sealants and adhesives at relatively low temperatures, providing excellent sag and slump resistance. Sealants and adhesives containing DISPARLON® TFS-10 exhibit superior viscosity stability during storage.

TYPICAL PROPERTIES

The following figures are typical properties, not to be used for specification.

Appearance	White to light yellow fine powder
Melting point	124 °C
Acid value (mgKOH/g)	Max. 6.0
Amine value (mgKOH/g)	Max. 6.0
Particle size	Max. 14 µm

ADVANTAGES

- Excellent sag and slump resistance
- High shear thinning
- Excellent workability and extrudability
- High tackiness and fast grab adhesiveness
- Suitable for cold-process production

APPLICATION

DISPARLON® TFS-10 is especially recommended for modified silicone and urethane sealants, as well as epoxy adhesives.

INCORPORATION

Addition levels

The recommended dosage level based on the total formulation is 0.5–5.0 wt%.

The optimal additive level should be determined under actual use conditions.

Method

The standard dispersing temperature is in the range of 40–70 °C.

Addition with a kneader, planetary mixer, or twin-screw extruder is recommended.

The optimal dispersing temperature, time, and shear should be determined under actual use conditions.

During the cooling process, high shear forces such as those generated by a high-speed dissolver should be avoided.



Kusumoto Chemicals, Ltd.

Kusumoto Bldg. 1-11-13 Uchikanda Chiyoda-ku Tokyo,
101-0047 Japan
TEL +81-3-3292-8685

<https://www.kusumoto.co.jp/en/>

The information provided herein is based on data believed to be reliable, but any recommendations or suggestions made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the condition that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by the user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement, or recommendation to practice any patented invention without a license. Please refer to the SDS for safe handling before use.
© 2024-2026 All Rights Reserved By Kusumoto Chemicals, Ltd.