



FINAWAX-B

DESCRIPTION : Behenamide

SPECIFICATIONS :

Appearance	:	Microbeads
Colour (Gardner)	:	2.0 max
Total Amide Purity	:	98 % min
Acid Value	:	1.0 max
Iodine Value	:	1.0 max
Melting Point	:	110 ± 5°C
Moisture	:	0.25% max

(Slight variations in the specifications stated due to raw materials and production conditions are possible though they have no influence on the application properties described.)

APPLICATIONS & PROPERTIES :

- Effective anti-block agent for Polyethylene/ Polypropylene film
- Improves film clarity
- Works synergistically with inorganic anti-blocks to improve clarity of PE/PP film

USE LEVEL : 0.5 - 2.0 %

The recommendations in this bulletin are made without guarantee since the conditions of use are beyond our control. Users should make their own tests depending on machinery available and desired properties.