Additives for coatings and printing inks



July 31, 2014 1/2P

DISPARLON[®] 6900-HV

(Anti-sagging / Anti-settling agent)

DISPARLON® 6900-HV is a paste of specially activated synthetic amide wax. It is easily incorporated into many vehicles and / or solvent and develops an exceptionally strong and long retained thixotropic structure.

ADVANTAGES

- Strong and long retained anti-sagging / settling properties.
- Little or no seeding, minimal affects on gloss and weather resistance.
- Less dependency on incorporation method for excellent dispersion.
- No need for precise temperature control and pregel preparation for the activation.
- Contributes to an improved orientation of metal pigment in wet film.
- Compatible with a wide range of solvents and vehicles.

APPLICATIONS

6900-HV can be used in almost all solvent based synthetic resin coatings. Particularly recommended are heavy duty paints such as Epoxies, Tar / epoxies, Urethanes, Chlorinated rubbers, Vinyls, Unsaturated polyesters, Acrylics and baking enamels such as Acrylic/Melamines for automotive top coat etc..

INCORPORATION

6900-HV is a paste consisting of activated particles in solvents. To obtain optimum activity, it is important to disperse **6900-HV** without destroying the original particles. Preferred is to disperse the additive with limited shear in a short period of time.

Additive levels

For anti-settling :	0.5 \sim 2.0% by weight on total formulation.
For anti-sagging :	$2.0\sim5.0\%$ by weight on total formulation.



Kusumoto Chemicals (Kunshan) Co., Ltd. NO.5 Jinfa Road, Jinxi Town, Kunshan City, Jiangsu Province, China Zip: 215300 Tel: (86)-512-57236788

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See MSDS for safety handling before to use.

Method

Post addition

Add in a finished paint and disperse with a high speed dissolver. To enable you to use this method, the paint worked on should have an initial viscosity of less than 70KU. The dissolver should be run at high speed with care taken so as to minimize air entrapment. This method is applicable to almost all types of low viscosity paints.

•Addition after Master batch preparation

A master batch may be prepared by dispersing the paste in a vehicle and/or solvent which can be added to the finished paint. This method is preferred for paints that are required to give a high quality surface and for metallic and flat paints formulated with specialty pigment such as Aluminum powder, Flatting agents, and Zinc dust.

Use of master batch is also recommended as an affective way to introduce thixotropy into Unsaturated polyester coatings or clear varnish coatings. For preparation of a master batch, the following recipe can be used: Resin / solvent / 6900-HV = 30% / 50% / 20%

The above mix is dispersed gently on Cowles type dissolver or three roll mill, until it reaches a particle size of 20 μ or less.

TYPICAL PROPERTIES

Appearance :	Light yellow paste
Non-volatile matter :	20% by wt.
Solvent:	Solvent naphtha / n-Butyl alcohol

CAUTION

6900-HV can cause poor recoatability when this products is used in forced dry or baking Oil based paints, Oil modified alkyds such as Melamine alkyd. Therefore **6900-HV** is not recommended for use in these systems.



Kusumoto Chemicals (Kunshan) Co., Ltd. NO.5 Jinfa Road, Jinxi Town, Kunshan City, Jiangsu Province, China Zip: 215300 Tel: (86)-512-57236788

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See MSDS for safety handling before to use.