

# DISPARLON

September 2021

## DISPARLON LAP-10, LAP-20, LAP-30

(Anti-popping/defoaming agents)

DISPARLON LAP-10 is anti-popping/defoaming agent based on vinyl polymer and acrylic polymer.  
DISPARLON LAP-20 and LAP-30 are anti-popping/defoaming agents based on an acrylic polymer.  
DISPARLON LAP-10, LAP-20 and LAP-30 are developed specifically for high-polar coatings like high-solid baking systems.

### ADVANTAGES

- Effective particularly in preventing popping associated with high-solid coatings involving methylated melamine, which is said to be difficult to control with conventional additives.
- In addition to the ability to prevent popping, these products can give leveling properties to the coating, thus eliminating the Benard-cell formation and floating.
- Silicone free/good recoatability.

### APPLICATIONS

As anti-popping agents

Applications	Recommended coating type
High-solid polyester (acrylic) melamine	Automotive, Coil, Electric appliance
Acid / Epoxy systems	Automotive (Clear top)
High-solid 2K urethane systems	Automotive (Clear top)

As defoaming agents

Applications	Recommended coating type
UV cured systems	Wood, Ink
Epoxy / Polyamide systems	Flooring

### INCORPORATION

Additive levels : 0.3 ~ 2.0 % by weight to total formulation.\*

\*The optimal level, however, should be determined by your laboratory tests.

Method : While this additive can be added at each production stage, post-addition at a final production stage stirring with a dissolver is recommended.

### TYPICAL PROPERTIES

	DISPARLON LAP-10	DISPARLON LAP-20	DISPARLON LAP-30
Appearance	Clear to light yellow liquid		
Non-volatile [%]	20% by wt.	20% by wt.	20% by wt.
Density	0.882	0.899	0.913
Viscosity	3.9mPa·s(cP)	2.7mPa·s(cP)	3.0mPa·s(cP)
Solvent	S-naphtha/n-Butyl acetate	n-Butyl acetate	n-Butyl acetate



Kusumoto Chemicals, Ltd.

11-13, UCHIKANDA 1-CHOME, CHIYODA-KU, TOKYO JAPAN  
(TEL) 81-3-3292-8685 (FAX) 81-3-3295-6079

The information on use is based on data which are believed reliable, but any recommendation or suggestion made are without guarantee or warranty, since the conditions of use are outside our control. All products are sold on the conditions that purchasers shall make their own tests to determine the suitability of such products for their purpose and that all risks are assumed by user. We disclaim any responsibility for damages resulting from careless or improper handling or use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. See SDS for safety handling before to use.

© 2009-2021 All Rights Reserved By Kusumoto Chemicals, Ltd.